

4 CONCLUSION

Based on the results obtained from the experimental investigation, the following conclusions have been drawn.

The natural gravel extracted from Jiren quarry site was not suitable for use as sub-base and base course material for road construction because it did not satisfy the requirements as per ERA Standard Specifications. The addition of 8% molasses in the natural gravel material from Jiren quarry site indicated suitable for sub-base construction, but not suitable as a stabilizer for base course. The addition of a minimum 2% lime in the natural gravel taken from Jiren quarry site was suitable for sub-base construction. On the other hand, replacing 50% of 8% lime with 4% molasses, 6% molasses or 8% molasses (4% Lime + 4% Molasses, 4% Lime + 6% Molasses and 4% Lime + 8% Molasses) produced adequate strength for base course construction.

Molasses alone cannot be used effectively to improve the natural gravel for use in base course construction. However, molasses can be used as an additive to lime in varying amounts which can provide satisfactory results meeting the required standards.

The blending of 6% lime with natural gravel increases the CBR by 205.64% Replacing 50% of 6% lime by 6% molasses and 8% molasses; blending the soil with 3%L + 6%M and 3%L + 8%M improved the natural gravel CBR by and 146.87% and 196.16% respectively. Further analysis, showed that blending 8% lime with natural gravel increased the CBR by 228.30%. Replacing 50% of 8% lime by 4% molasses, 6% molasses and 8% molasses; blending the natural gravel with 4%L + 4%M, 4%L + 6%M and 4%L + 8%M improved the natural gravel CBR by 190.84%, 210.72% and 227.34% respectively.

Finally, it is known that the curing process plays an important role in the development of strength of molasses-lime stabilized natural gravel. The increase in CBR value corresponded to the blend of natural gravel with 4% lime plus 8% molasses after 14 days of curing found to be 347.44%. The natural gravel treated with molasses-lime achieved an average of 293.8 percent CBR after 14-days curing of the untreated CBR of 28.16%. The CBR of the molasses-lime treated natural gravel at a curing time of 3 days achieved an average CBR about 81% of the 14 days curing, and at a curing time of 7 days achieved an average CBR about 95.62% of the 14 days curing period.

ACKNOWLEDGMENT

The authors wish to thank the Jimma Institute of Technology, Jimma University for sponsoring this research.

REFERENCES

- [1] Basha, E. A., R. Hashim, H. B. Mahmud, and A. S. Muntohar (2005). Stabilization of Residual Soil with Rice Husk Ash and Cement. *Construction and Building Materials*, Vol. 19, pp. 448-453.
- [2] ARBA. American Road Builders (1996), *Materials for Stabilization*, Washington, D.C.
- [3] Gow, A. J., D. T. Davidson, and J. B. Sheeler (2001). Relative Effects of Chlorides, Lignosulfonates and Molasses on Properties of a Soil-Aggregate Mix. In *Highway Research Record 282*, HRB, National Research Council, Washington, D.C., pp. 66-83.
- [4] Suriadi, A., Murray, R. S., Grant, C. D. & Nelson, P. N. (2002) Structural stability of sodic soils in by gypsum and molasses. *Australian Journal of Experimental Agriculture*, 42: 315-322.
- [5] Almaz Ejeta, Emer Tucay Quezon, Habtamu Getachew (2017). Engineering Properties of Mechanically Stabilized Subbase Material Using Natural Gravel around Jimma Quarry Sites for Unpaved Road Construction; *Global Scientific Journals*: Vol 5, Issue 5, pp. 93-102.
- [6] Ethiopian Road Authority (2002), *Pavement Design Manual, Flexible Pavements, and Gravel Roads*, Unbound Pavement Materials, Addis Ababa.
- [7] Little, D.N (1995). *Handbook for Stabilization of Pavement Subgrades and Base Courses with Lime*. Kendall/Hunt, Iowa.
- [8] Joint Departments of the Army and Air Force (JDAAF) (1994). *Soil stabilization for pavements*, TM 5-822-14/AFMAN 32-8010, Washington, DC.
- [9] B. I. Siswosoebrotho, M. Hossain, A. Alias and B. K. Huat (2004), "Stabilization of tropical residual soils," Taylor and Francis Group, pp145-167.

- [10] Air Force Civil Engineer, (2012). Military Soils Engineering. Chapter 9, Soil Stabilization for Roads and Airfields. Field Manual, 5-410p.
- [11] National lime association (2004). Lime stabilization and lime modification. Published report.41p.
- [12] American Road Builders Association, (2004). Lime-treated Soil Construction Manual. Published report. 40p.
- [13] Bulbul A., Abdul A., Abu S. (2013). Improvement of Soil Strength Using Cement and Lime Admixtures. Earth Science. 2 (6): 139-144.
- [14] Miura N., Horpibulsuk S., and Nagaraj T.S. (2002). Engineering behavior of cement stabilized clay at high water content. Soils and Foundations, Japan Geotechnical Society (JGS). 41(5): 33-45.
- [15] Hassnen M. J. (2013). Stabilization of Soft Soils Using Salts of Chloride. Journal of Babylon University/Engineering Sciences/ No.(5)/ Vol.(21).
- [16] Tamadher T.A., Anuar B.K., Zamri B.C. (2007). Stabilization of Silty Clay Soil using Chloride Compounds. Engineering Science and Technology. 2(1):102-110.
- [17] M'Ndegwa, J.K. (2011). The Effect of Cane Molasses on the strength of Expansive Clay Soil. Emerging Trends in Engineering and Applied Sciences. 2 (6): 1034-104.
- [18] O'Neill J.M. (2011). Molasses used in the cleanup of polluted sites. Published report. North Jersey.
- [19] ASTM D 422-63, 2002. Standard Test Method for Particle-Size Analysis of Soils. Annual Book of ASTM Standards, Vol. 04.08, West Conshohocken, PA.
- [20] ASTM D 558-96, 2002. Standard Test Methods for Moisture-Density Relations of Soil-Cement Mixes. Annual Book of ASTM Standards, Vol. 04.08, West Conshohocken, PA.
- [21] ASTM D 4318-00, 2002. Standard Test Methods for Liquid Limit, Plastic Limit, and Plasticity Index of Soils. Annual Book of ASTM Standards, Vol. 04.08, West Conshohocken, PA.
- [22] ASTM D 4643-00, 2002. Standard Test Method for Determination of Water (Moisture) Content of Soil by the Microwave Oven Heating. Annual Book of ASTM Standards, Vol. 04.08, West Conshohocken, PA.