

- The longitudinal and transverse residual stress value conforms that the residual stress are changed from compressive to tensile on the coated specimen surface in the D-gun coating process.
- Among all coated substrate ATG2 coated substrate has lesser tensile residual stress in longitudinal and transverse direction.

6 References

- 1 **Pawlowski L**, *The Science and Engineering of Thermal Spray Coatings*, John Wiley and Sons, Chichester, 1995.
- 2 **Kingery W D**, *Introduction to ceramics*, 1960, John Wiley & Sons, Inc., New York, London.
- 3 **Kharlamov Y.A.** Material engineering forum. Detonation spraying of protective coatings, *Material Science and Engineering* 93 (1987) 1–37.
- 4 **Kharlamov Y.A.**, Bonding of detonation-sprayed coatings, *Thin Solid Films* 54 (3) (1978) 271– 278.
- 5 **Sundaram Rajakumar, L. Vijayaraghavan and M. M. Mayuram**, “Flexure Response of D-Gun Sprayed Functionally Graded Coating of Alumina and Alumina-Titania Ceramic Composite”, Proceeding of the 2nd International & 23rd All India Manufacturing Technology, Design and Research Conference (AIMTDR ‘08), pp.183-188, December 15-17, 2008, IIT-Madras, Tamilnadu, India.