

REFERENCES

- Altoubat S. and Lange D. (2002), "The picket effect at early age and experiment separating its mechanism in tension," *Materials and Structures*, vol. 35, no. 4, 2002.
- Bazant Z. and Osman E. (1976), "Double power law of basic creep of concrete," *Materials and Structures*, vol. 9, no. 1. Pp 3-11
- Bazant Z. and Chern J. (1985), "Concrete creep at variable humidity: constitutive law and mechanism," *Materials and Structures*, vol. 18. Pp 1-20
- Bazant Z. and Robert L. (1988), "Mathematical modeling of creep and shrinkage of concrete," Wiley, 1988.
- Bazant Z. and Yunping X. (1994), "Drying creep of concrete: constitutive model and new experiments separating its mechanisms," *Materials and Structures*, vol. 27, no. 1. Pp 3-14
- BS EN 12350: 2000, Testing Fresh Concrete - Part 2: Slump Test. BSI, London, United Kingdom; 2000.
- BS EN 12390: 2001, Testing Hardened Concrete - Part 2: Making and Curing Specimens for Strength Tests. BSI, London, United Kingdom. 2001
- BS EN 12390. Testing Hardened Concrete-Part 3: Compressive Strength of Test Specimens. BSI, London, United Kingdom. 2001
- BS 1881-102: 1983, Testing Concrete. Method for Determination of Slump. BSI, London, United Kingdom. 1983
- BS 1881-103: 1983, Testing Concrete. Method for Determination of Compacting Factor. BSI, London, United Kingdom. 1983
- BS 1881-107: 1983, Testing Concrete. Method for Determination of Density of Compacted Fresh Concrete. BSI, London, United Kingdom. 1983
- Neville A. and Brooks J. (2010), "Concrete Technology," Prentice-Hall.
- Paulo L.B. and Pina-Henriques J. (2007), "3. Collapse prediction and creep effect.".
- Wittman F. and Roelfstra P. (1980), "Total deformation of loaded drying concrete," *Cement and Concrete Research*, vol. 10, no. 5. Pp 601-610
- Wittman F. (1993), "On the influence of stress on shrinkage of concrete," in *RILEM PROCEEDINGS. CHAPMAN AND HALL*. Pp 151

Appendix

CREEP
 STRAIN READINGS

Days	Time	Up	Down	Left	Right	Temperature °c	Relative Humidity %
7	12:35pm	0.02	0	0	0.26	30	85
10	1:18pm	0.03	0	0.04	0.18	30	85
11	09:54am	0.04	0	0.04	0.18	29	95
12	12:30pm	0.04	0	0.04	0.18	30	88
13	12:30pm	0.04	0	0.04	0.18	29	92
14	12:30pm	0.04	0	0.04	0.11	32	86
19	02:10pm	0.04	0	0.04	0.1	30	90
20	11:30am	0.04	0	0.04	0.1	28	85
22	10:10am	0.04	0	0.04	0.09	28	70
23	10:50am	0.04	0	0.04	0.08	28	70
25	10:53am	0.04	0	0.04	0.08	29	58
26	12:30pm	0.04	0	0.04	0.14	35	94
27	10:28am	0.04	0	0.04	0.15	25	80
28	11:40am	0.04	0	0.04	0.16	28	80
31	12:20pm	0.06	0	0.04	0.09	34	86
32	11:30am	0.06	0	0.04	0.09	30	82
33	11:24am	0.06	0	0.04	0.09	30	85
34	1:04pm	0.06	0	0.04	0.09	37	90
35	1:10pm	0.06	0	0.04	0.09	36	88
38	12:07pm	0.06	0	0.04	0.09	30	82
39	11:30am	0.06	0	0.04	0.09	26	76
40	10:40am	0.06	0	0.04	0.08	28	79
41	11:26am	0.05	0	0.04	0.08	30	84
42	10:32am	0.05	0	0.04	0.08	30	80
47	9:00am	0.05	0	0.04	0.06	27	88
48	9:30am	0.05	0	0.04	0.05	26	88
49	10:47am	0.05	0	0.04	0.05	29	88
52	9:50am	0.05	0	0.04	0.05	27	88
53	1:16pm	0.05	0	0.04	0.04	29	82
54	12:23pm	0.06	0	0.04	0.04	28	86
55	8:51am	0.06	0	0.04	0.04	28	90
56	11:42am	0.06	0	0.04	0.04	29	88
59	12:38pm	0.06	0	0.04	0.04	30	88
60	11:11am	0.06	0	0.04	0.04	30	86
61	10:09am	0.06	0	0.04	0.04	29	90
62	4:05pm	0.06	0	0.04	0.03	30	82
63	2:00pm	0.06	0	0.04	0.03	30	86
66	9:48am	0.06	0	0.04	0.03	30	90

67	10:35am	0.06	0	0.05	0.03	30	90
68	3:02pm	0.06	0	0.05	0.03	30	88
69	11:00am	0.06	0	0.05	0.02	30	90
70	2:35pm	0.06	0	0.05	0.02	29	88
73	3:48pm	0.06	0	0.05	0.02	30	78
74	10:27am	0.06	0	0.05	0.02	28	90
75	3:11pm	0.06	0	0.05	0.02	30	80
76	4:29pm	0.06	0	0.05	0.01	30	80
77	1:38pm	0.06	0	0.05	0.01	30	80
80	9:09am	0.06	0	0.05	0.01	28	88
83	10:48am	0.06	0	0.05	0	28	80

© GSJ